

Technical Data Sheet – WSR 28 Semi rebonded Magchrome

Magnesia chrome brick

Product

Item code:	WSR-28
Product:	WSR 28 Semi rebonded Magchrome
Family:	Magnesia chrome brick
Tariff number:	6902.10.1000
Origin:	China
Unit:	Metric ton
Metric tons:	19.96 in a 20 foot container; 20.4 in a 40 foot container

Specification

Property	Unit	Value
Aluminium oxide	%	9 typical
Apparent porosity	%	17.6 typical
Bulk density	g/cm ³	3.17 typical
Calcium oxide	%	1.5 typical
Chromium oxide	%	29 typical
Cold crushing strength	MPa	50 typical
Iron oxide	%	16.6 typical
Magnesium oxide	%	43.1 typical
Refractoriness under load	°C	1700 typical
Silicon dioxide	%	1.5 typical

Typical values are for guidance and are not a guarantee. Limits marked min or max apply to each shipment, confirmed by the certificate of analysis. Test methods on request.